


FERRITE CORE | POT-Core

磁芯品名规则说明 (例)
SMP40 P9/5 - Z 或 A200

材料 磁芯材料: A 磁芯: Z 或 A200 ALU002AL000H000...



品名	形状	尺寸规格(Unit: mm)											磁芯常数	等效截面面积	最小等效截面面积	等效磁路长度	等效体积	重量	电气特性						
		磁芯形状	材料	图示	A	E	F	H	2B	2D	C	G							I	J	K	L	M	N	O
1	P3.3/2.6	SMP40	Fig.1	3.24±0.06	2.55±0.05	1.35±0.05							2.55±0.05	1.8±0.1	1.05	3.136	1.77	1.43	5.56	0.070	0.100	无气隙	带		
2	P4.6/3.1	SMP40	Fig.1	4.5±0.1	3.575±0.075	1.95±0.05							3.05±0.05	2.2±0.1	1.4	2.088	3.43	2.60	7.16	24.6	0.200	无气隙	带		
3	P5.8/3.3	SMP40	Fig.1	5.725±0.075	4.55±0.05	2.45±0.05							1.00±0.05	3.25±0.05	2.3±0.1	1.7	1.632	4.73	3.66	7.72	36.5	0.4	无气隙	带	
4	P7/4	SMP40	Fig.1	7.25±0.10	5.875±0.075	2.9±0.1							1.10±0.05	4.05±0.05	2.9±0.1	1.9	1.358	7.27	5.79	9.88	71.0	0.60	无气隙	带	
5	P9/5	SMP40	Fig.2	9.15±0.15	7.65±0.15	3.8±0.1							2.1±0.1	5.25±0.15	3.75±0.15	6.75	2	1.215	10.20	7.88	12.40	126	0.8	无气隙	带
6	P11/7	SMP40	Fig.2	11.1±0.2	9.2±0.2	4.6±0.1							2.1±0.1	6.45±0.15	4.55±0.15	7.25	2.2	0.942	16.40	13.320	15.550	25.5	1	无气隙	带
7	P14/8	SMP40	Fig.2	14.05±0.25	11.8±0.2	5.9±0.1							3.1±0.1	8.35±0.15	5.8±0.2	9.35	3.2	0.766	25.60	19.80	19.60	30.2	1	无气隙	带
8	P18/11	SMP40	Fig.2	18.0±0.4	15.1±0.25	7.4±0.15							4.1±0.1	10.5±0.15	7.4±0.2	12.65	3.5	0.539	44.50	26.90	25.20	40.0	1	无气隙	带
9	P22/13	SMP40	Fig.2	21.6±0.4	18.2±0.3	8.9±0.15							4.55±0.15	13.35±0.15	9.35±0.15	14.9	3.7	0.485	64.70	50.90	31.30	50	1	无气隙	带
10	P26/16	SMP40	Fig.2	25.5±0.5	21.6±0.4	11.3±0.2							5.55±0.15	16.1±0.2	11.2±0.2	18.5	3.7	0.392	95.70	76.10	37	50	1	无气隙	带
11	P30/19	SMP40	Fig.2	30.0±0.5	25.4±0.4	13.3±0.2							5.55±0.15	18.8±0.2	13.2±0.2	21.5	4.4	0.320	138.00	113.00	42	50	1	无气隙	带
12	P36/22	SMP40	Fig.2	35.6±0.6	30.4±0.5	15.9±0.25							5.55±0.15	21.4±0.2	14.0±0.2	25.6	4.9	0.250	195.20	105.00	52	50	1	无气隙	带